Catalytic Wet Air Oxidation of High BPA Concentration Over Iron based Catalyst Supported on Orthophosphate

Fatiha Kaissouni¹, Rachid Brahmi^{2*}, Mohamed Zbair¹, Gwendoline Lafaye⁴, Zouhair El Assal³,
Laurence Pirault-Roy⁴, Jacques Barbier Junior⁴, Abdelkrim Elaissi¹, Mohammed Bensitel¹,
Mohammed Baalala¹

¹Laboratory of Catalysis and Corrosion of Materials, Department of Chemistry, University
Chouaïb Doukkali, Avenue des Facultés, 24000 El Jadida -Morocco.

²Laboratory of Coordination and Analytical Chemistry (LCCA), University Chouaïb Doukkali,
Avenue des Facultés, 24000 El Jadida -Morocco.

³Faculty of Technology, Environmental and Chemical Engineering, University of Oulu, P. O. Box
4300, FI-90014 Oulu, Finland.

⁴IC2MP UMR 7285 CNRS, University of Poitiers, 4 rue Michel Brunet, 86022 Poitiers Cedex,
France.

* Corresponding author: rachid.brahmi@univ-poitiers.fr

Acknowledgments

We gratefully acknowledge the financial support provided by the European communities (FEDER), the “Region Nouvelle Aquitaine”, and the Project Partenariats Hubert Curien (PHC) Maghreb program (16MAG11) for funding Miss Kaissouni's internships at IC2MP, Poitiers-France.

32 **Abstract**

33 The catalytic performance of Fe supported on nickel phosphate (NiP) was evaluated for the removal
34 of Bisphenol A (BPA) by catalytic wet air oxidation (CWAO) at 140°C and 25 bar of pure oxygen
35 pressure. The prepared NiP and Fe/NiP materials were fully characterized by XRD, N₂-
36 physisorption, H₂-TPR, TEM, and ICP analysis. Iron (Fe/NiP) impregnation of NiP support
37 enhanced the BPA removal efficiency from 37.0 % to 99.6 % when CWAO was performed. This
38 catalyst was highly stable given the operating conditions of acidic medium, high temperature and
39 high pressure. The Fe/NiP catalyst showed an outstanding catalytic activity for oxidation of BPA,
40 achieving almost complete removal of BPA in 180 min at a concentration of 300 mg/L, using 4 g/L
41 of Fe/NiP. No iron leaching was detected after the CWAO of BPA. The stability of Fe/NiP was
42 performed over three consecutive cycles, noting that BPA conversion was not affected and iron
43 leaching was negligible. Therefore, this catalyst (Fe/NiP) could be considered as an innocuous and
44 effective long-lasting catalyst for the oxidation of harmful organic molecules.

45 **Keywords:** Bisphenol A; CWAO; Oxidation; Catalyst; iron-Nickel Phosphate; Environment.

46

47 **Abbreviations:**

48	WAO	: Wet Air Oxidation
49	CWAO	: Catalytic Wet Air Oxidation,
50	BPA	: Bisphenol A,
51	EDC	: Endocrine Disrupting Chemical
52	AOPs	: Advanced Oxidation Processes,
53	XRD	: X-Ray Diffraction,
54	H₂-TPR	: Temperature-Programmed Reduction,
55	ICP-OES	: Inductively Coupled Plasma Optical Emission Spectroscopy,
56	TEM	: Transmission Electron Microscopy,
57	TOC	: Total Organic Carbon,
58	COD	: Chemical Oxygen Demand,
59	HPLC	: High Performance Liquid Chromatography,
60	PFO	: Pseudo-First-Order.

61

1. Introduction

Bisphenol A (BPA) is a synthetic organic compound with two unsaturated phenolic rings attached by a bridging carbon. BPA is classified as an endocrine-disrupting chemical (EDC) with estrogenic properties, but it is still widely used as a plasticizer in the synthesis of polycarbonate plastics and epoxy resins (Ben-Jonathan and Steinmetz, 1998) because it is very durable; heat and shatter resistant, and can also improve the clarity of plastics. It is widely used in the manufacture of some food and beverage packaging, e.g., water and baby bottles, compact discs, dental sealants, medical devices and lacquers for coating metal products such as plastic cans, bottle caps and water pipes (Chapin et al., 2008; Chouhan et al., 2014). Thus, humans ingest BPA on an almost daily basis. It is known that babies and children are more affected by BPA than adults. BPA has been detected in urine and serum of pregnant women and in placental tissue, amniotic fluid and urine of babies (Vandenberg et al., 2007). In addition, BPA has also been detected in wastewater, groundwater, surface water and even drinking water (Lane et al., 2015; Lee et al., 2015; Zbair et al., 2018). Recent studies have indicated that the estrogenic activity of BPA at levels as low as 0.2 pg/mL causes endocrine disruption leading in infertility, breast cancer and thyroid cancer (Gültekin and Ince, 2007). There is therefore an urgent need to develop effective technology to remove BPA from wastewater and drinking water.

Up to date, a number of methods such as adsorption, biological treatment and advanced oxidation have been investigated to remove BPA from water (Anastopoulos et al., 2017; Mohapatra et al., 2010; Zbair et al., 2018). Biological treatment would be the least expensive, but it takes longer to remove BPA (Lobos et al., 1992; Omoike et al., 2013). Moreover, conventional biological management appears to have a low and unstable BPA removal capacity due to its very low concentration in water and high biorefractory properties (Cleveland et al., 2014; Staples et al., 1998). The adsorption process is simple and efficient, but it requires high operating costs related to the regeneration of spent adsorbents from contaminants (Cleveland et al., 2014). On the other hand, advanced oxidation processes (AOPs) have demonstrated a great capacity to degrade persistent organic matter through the formation of highly active oxidizing free radicals (HO and SO_4^-) (Athalthil et al., 2015; Reddy and Kim, 2015). Among the processes of AOPs tested for the elimination of BPA, it can be mentioned: UV/ H_2O_2 process (Moussavi et al., 2018), electro-generated ferrous ion activated ozone, H_2O_2 and persulfate system (Akbari et al., 2016), Fenton like process (Ahmadi et al., 2016; Arampatzidou et al., 2018) and catalytic wet air oxidation (CWAO) method (Erjavec et al., 2013). CWAO is a particularly effective and promising process for removing organic compounds, such as phenolic compounds, from wastewater (Keav et al., 2014;

95 Nousir et al., 2008). Moreover, CWAO is an industrially feasible and environmentally-friendly
96 system that destroys organic contaminants as biodegradable intermediates or mineralizes them into
97 CO₂, H₂O and harmless end-products at high temperature (125–320 °C) and under oxygen or air
98 pressure (0.5–20 MPa). Noble metals supported on oxides or carbon materials are widely studied in
99 CWAO because of their high catalytic performance and resistance to metal leaching (Kim and Ihm,
100 2011; Levec and Pintar, 2007). However, the high cost and scarcity of these precious metals make it
101 necessary to explore new routes to either minimize their use or replace them with non-noble
102 catalysts with similar catalytic properties. For example, a titanium nanotube catalyst proved to be
103 very effective for the destruction of BPA by CWAO. It showed a high activity of about 91% and a
104 Total Organic Carbon (TOC) abatement of 69% (Kaplan et al., 2014a), with the end products
105 being mostly biodegradable compounds. In addition, CeO₂ and Ce_{0.85} Zr_{0.15}O₂ catalysts achieved
106 76% BPA conversion and 75% and 73% TOC abatement, respectively (Heponiemi et al., 2015).

107 Phosphate-based materials have been of great interest in recent years as they can be used as
108 fertilizers, catalysts, ion conductors, piezoelectric materials, biotechnological materials and
109 sorbents. Currently, there is more interest in the use of these materials as catalysts for various
110 chemical transformations. The novelty of this research is the investigation of inexpensive Iron-
111 Nickel-Phosphate oxide based catalysts in the catalytic wet air oxidation of an aqueous solution of
112 Bisphenol A. The activity of the catalyst (Fe/NiP) and its stability were studied for the removal of
113 Bisphenol A (BPA) by catalytic wet air oxidation (CWAO). The objective is to identify the features
114 of the catalyst that will influence the activity and selectivity of the reaction.

115 **2. Materials and methods**

116 **2.1. Preparation of nickel phosphate support (NiP)**

117 The support was prepared by co-precipitation method using the required stoichiometric amount of
118 aqueous solutions of the precursor salts Ni(NO₃)₂·6H₂O (Sigma-Aldrich Chemical company, 99%
119 purity) and (NH₄)₂HPO₄ (Sigma-Aldrich chemical Company, 99% purity). The Ni(NO₃)₂·6H₂O salt
120 solution was added dropwise to the ammonium hydrogenophosphate solution under continuous
121 stirring. The pH was then adjusted to 9 with ammonia solution (25%, Sigma-Aldrich chemical
122 Company), the mixture was left under constant stirring for 3 hours. The obtained co-precipitate
123 solution was dried overnight at 120°C and calcined under air flow at 450°C for 8 hours with a
124 temperature rise of 5°C min⁻¹. The resulting support was labeled NiP.

2.2. Deposition of the iron active phase

The wet-impregnation method was used to deposit 20 wt-% of iron from an aqueous solution of $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$ (Sigma-Aldrich, 99%). The support was brought into contact with the necessary volume of iron solution. The mixture of Fe precursor solution and the support was stirred overnight and dried at 60°C until the excess water evaporated completely. Finally, the dried sample was calcined in an air atmosphere for 3 hours at 450°C with a ramp of 5°C min^{-1} .

2.3. Characterization methods

The X-ray diffraction (XRD) analysis of NiP and Fe/NiP was performed using a Bruker-BINARY, model D8 Diffractometer, equipped with a $\text{Cu K}\alpha$ radiation ($\lambda_{\text{K}\alpha} = 1.5418 \text{ \AA}$). Both samples were scanned in the range 2θ from 15 to 70° with a 0.02° step in 30 s.

The specific surface areas, pore volume and pore size distribution of NiP and Fe/NiP were measured by nitrogen physisorption at -196°C using a Micrometrics TRISTAR 3000 device applying successively the BET and the BJH models. Prior to these measurements, the samples were degassed under vacuum at 250°C overnight to clean the surface of the materials.

H_2 -TPR (temperature-programmed reduction) measurements were performed on an Autochem II 2920 with a 10% H_2/Ar gas mixture and a flow rate set at 50 mL/min . Prior to the measurements, the samples were pretreated under Ar at 450°C for 1h, with a temperature ramp of 10°C/min , and then cooled down to room temperature. H_2 -TPR analysis was performed from room temperature to 850°C with a ramp of $10^\circ\text{C min}^{-1}$.

The Fe content of the prepared catalyst (Fe/NiP) was determined by inductively coupled plasma optical emission spectroscopy (ICP-OES). The analysis was performed using a Perkin-Elmer Optima 2000DV. Prior to analysis, a known mass of sample powder was dissolved in acid under microwave heating. The ICP analysis was also used to analyze the leaching of iron in aqueous solution after CWAO reaction.

The surface morphology of NiP and Fe/NiP were observed by transmission electron microscopy using a "TEM / STEM JEOL 2100 UHR", with a resolution of 0.19 nm , equipped with an EDAX energy dispersive spectrometer, a HAADF wide angle annular dark field detector and Gatan CCD camera.

2.4. Catalytic experiments

CWAO experiments were investigated in a 0.44 L batch reactor made of Hastelloy C22 alloy loaded with 160 mL of BPA solution (0.3 g/L) and NiP or Fe/NiP catalyst (4 g/L). After a purge with helium, the reactor was heated up to the reaction temperature. The stirring speed was set at 1000

rpm. At the initial time of the reaction, 25 bars of pure O₂ were introduced into the reactor. The pressure was kept constant during the experiment by regular refilling with O₂. Samples of the liquid phase were periodically collected and filtered through a Durapore membrane (0.45 µm; Ø = 13 mm) to remove all catalyst residues for analysis. The liquid samples were analyzed by HPLC using a 250 × 4.6 mm C18 reversed-phase column (Shimadzu Prominence UFLC_{XR}). The mobile phase was a mix of 60 vol. % methanol and 40 vol. % water (flow rate: 0.8 mL/min). The HPLC system was equipped with a UV-visible detector fixed at 276 nm. Total Organic Carbon (TOC) values were determined using a total organic analyzer Shimadzu LCPH/CPN. The HPLC and TOC devices are calibrated using standard solutions of Bisphenol A in ultra-pure water. At the end of the CWAO reaction (180 min), the reactor was cooled down to room temperature. ICP analysis of the remaining solutions was performed to ensure that iron did not leach from the Fe/NiP catalyst. It is worth noted that the reproducibility of the experimental protocol was proved for several reference catalysts and that the experimental error was found to be less than 5%.

3. Results and Discussion

3.1.Characterization of samples

X-ray diffraction was used to identify crystalline phases formed in NiP support and Fe/NiP catalyst. **Fig. 1a** shows the XRD patterns of NiP and Fe/NiP samples which display amorphous phases and semi-crystalline peaks. By comparison with ICDD database (International Centre for Diffraction Data), it appears that the main crystalline phase on the NiP support is a monoclinic structure of Ni₃(PO₄)₂ (ICDD: 00-038-1473). As expected, the XRD pattern of Fe/NiP catalyst reveals the presence of Ni₃(PO₄)₂ phase. It presents also a hydrated phase of iron sulfate hydroxide ((Fe_{1.33}²⁺Fe_{0.67}³⁺(SO₄)₂(OH)_{0.67}·xH₂O) (ICDD: 00-053-1056), as well as unidentified phases. The amount of iron impregnated on NiP support, determined by ICP analysis, is 18.5 wt-% (**Table 1**), which is close to the target value (20 wt-%).

According to IUPAC Classification (Sing, 1985) , the N₂-physorptions on NiP and Fe/NiP evidence type IV isotherms indicating the presence of mesopores (**Fig. 1b**). Both isotherms exhibit type H3 hysteresis loop, indicating the presence of non-rigid aggregates of plate-like particles or assemblages of slit-like pores.

For comparison purposes, the specific surface area, the total pore volume, and the average pore diameter obtained from nitrogen physisorption isotherms of NiP and Fe/NiP are summarized in **Table 1**. All the textural parameters decrease after the impregnation of iron, suggesting that iron particles partially block NiP support pores.

Fig. 1: XRD patterns (a) and Nitrogen adsorption-desorption isotherms (b) of NiP and Fe/NiP.

Table 1. Textural parameters and ICP analysis of NiP and Fe/NiP.

Sample	S _{BET} (m ² /g)	Total pore volume (cm ³ /g)	Average pore diameter (nm)	Fe Content (wt-%)
NiP	66	0.18	10.8	-
Fe/NiP	21	0.05	9.2	18.5

H₂-Temperature Programmed Reduction (H₂-TPR) was performed on the samples. **Fig. 2** shows the hydrogen uptakes as a function of temperature, obtained for NiP (**Fig. 2a**) and Fe/NiP (**Fig. 2b**). The decomposition of the TPR profile of NiP reveals several peaks located around 407, 444, 543, 645, 725, 781, and 820°C (**Fig. 2a**). According to the literature, the peaks at 407°C and 444°C can be attributed to the reduction of small and large crystallites of NiO to Ni metallic, respectively (Bui et al., 2012; Chen et al., 2014; Pan et al., 2016; Zou et al., 2018). The peak at 543°C is related to the phosphidation of nickel (Bui et al., 2012). Furthermore, the peak at 645°C can be assigned to the reduction of nickel oxy-phosphate (Chen et al. 2014). In addition, the peaks at 725, 781, and 820°C could be due to the reduction of nickel oxy-phosphate, nickel phosphate and P-O bond (Bui et al., 2012; Chen et al., 2014; Pan et al., 2016).

Fig. 2b shows that the addition of iron to NiP strongly modifies the shape of the TPR profile of NiP (**Fig. 2a**). Decomposed TPR curve of Fe/NiP displays four peaks at 460, 482, 524 and 770°C. The reduction temperature of NiO to metallic Ni shifts slightly to a higher temperature in the presence of Fe. This slight increase from 444°C to 460°C is consistent with the literature (Zou et al., 2018) and

206 is explained by an interaction between Ni and Fe. The peak at 482°C can be assigned to the
 207 reduction of Fe_2O_3 to Fe_3O_4 (Chen et al., 2014; Pan et al., 2016) and the peak at 524°C can be
 208 attributed to the co-reduction of Fe_2O_3 and Fe_3O_4 to FeO and Fe (Zhang et al., 2018; Zou et al.,
 209 2018). Finally, the peak at 770°C can be due to the reduction of iron-phosphate (Chen et al., 2014)
 210 or the co-reduction of nickel and iron associated with phosphate (Pan et al., 2016).

Fig. 2: H₂-Temperature Programmed Reduction profiles of (a) NiP (b) Fe/NiP.

The Transmission Electron Microscopy (TEM) images of NiP and Fe/NiP are shown in Fig.3. As it can be seen in Fig. 3a and 3b, NiP exhibits an amorphous nano-cylindrical morphology with different thicknesses ranging from 13 to 49 nm. In addition, the TEM images also indicate the presence of interconnected mesopores. The distribution of particle size is centered at 5.5 nm (Fig. 3c). In contrast, after the impregnation of Fe on NiP, the nano-cylindrical morphology and the porosity are not observed (Fig. 3d), this can be explained by the high dispersion of Fe (yellow color) on the surface of NiP. Indeed, the map analysis of the Fe/NiP sample (Fig. 3e) shows the homogenous distribution of Fe on the NiP surface. Furthermore, the mapping analysis reveals the presence of sulfur (green color), which is present in the active phase ((Fe_{1.33}²⁺Fe_{0.67}³⁺(SO₄)₂(OH)_{0.67}·xH₂O)), already identified by XRD. This result is therefore in good agreement with N₂-physisorption analysis, which reveals a decrease in surface area due to the clogging of pores by Fe particles.

Fig. 3 (a) and (b): TEM images of NiP, (c): Distribution of particle size, (d): TEM of Fe/NiP, and (e): TEM-mapping.

3.2. Catalytic results

3.2.1. Thermal decomposition (blank tests)

The temperature plays a very important role in the WAO process of degradation of hazardous organic pollutants. Thus, the rate of reaction, the total reduction of TOC and COD are highly dependent on the temperature (Kaplan et al., 2014b; Pintar et al., 2008). Moreover, the mechanism of degradation of organic pollutants in the WAO process is also strongly related to the reaction temperature due to the various types of free radicals that can be generated (Pintar et al., 2008). For this reason, blank experiments i.e without a catalyst, were carried out to study the thermal decomposition of BPA at 140°C. Fig. 4a displays BPA conversion as a function of time. Blank test shows that the conversion of BPA after 180 min at 140°C reaches only 37.0 % and leads to many by-products, as shown on the HPLC chromatogram displayed in Fig. 4b. This result is explained by the fact that the aromatic structure of the phenolic compounds gives them a high activation energy for WAO. Consequently, higher reaction temperature is required to get over such high activation energy barriers (Mirzaee et al., 2018). In order to avoid excessive temperature conditions and thus reduce the cost, the use of a catalyst is necessary to improve the conversion of BPA and to avoid the formation of by-products.

Fig. 4 (a) Thermal decomposition of BPA at 140 °C (b) HPLC chromatogram for WAO of BPA (without catalyst).

3.2.2. Effect of support and catalyst

First, the NiP support was tested to evaluate its performance for CWAQ of BPA. Fig. 5a shows that BPA conversion after 180 min of reaction (37 %) is similar to that obtained with the blank test at 140°C. On the other hand, the modification of NiP by Fe induces a significant increase in catalytic

properties. Fe/NiP exhibits a good catalytic activity since the BPA is fully converted (99.8 %) after 180 min of reaction (**Fig. 5a**) and 85 % Δ TOC are achieved (**Table 2**) versus only 35 % with NiP. Nevertheless, BPA was not entirely transformed into carbon dioxide, which implies the formation of some organic intermediates.

Liquid phase samples were periodically collected during the CWAQ process for analysis by HPLC for the blank test, NiP and Fe/NiP. The conversion curves are displayed in Fig. 5a. The HPLC chromatograms focused on the BPA peaks were illustrated in **Fig. 5b, c and d**. The inset figures (**Fig. 5b, c and d**) showed the temporal evolution of the spectral changes of BPA generated by HPLC of BPA conversion using NiP and Fe/NiP samples. With the reaction time, the peak intensity of BPA gradually decreases. BPA is fully converted after 180 min for Fe/NiP. The disappearance of BPA is accompanied by the formation of its by-products similarly to that is observed in Fig. 4b. The formation of these by-products is in accordance with the values of Δ TOC.

Comparison of the HPLC chromatograms (**Fig. 6a, b**) after 180 min of reaction shows that several intermediates are detected in the case of NiP while only two peaks are detected in the case of Fe/NiP. These peaks are detected at a shorter retention time than that of BPA, indicating that the intermediates produced are more polar than BPA. This is in agreement with the results stated in the previous study on the degradation of BPA (Tai et al., 2005). However, all detected peak areas of the BPA intermediates were much lower than those of the initial BPA. In other words, fluctuations of these BPA intermediates as a function of time reveal different possible step in the degradation pathways of BPA, and it is, therefore, difficult to identify them. Although the study does not aim to analyze in detail the by-products obtained during the CWAQ of BPA, the main products detected were tentatively identified in comparison to the studies of Miho Sasaki et al (Sasaki et al., 2005b, 2005a), Vincent Cleveland et al (Cleveland et al., 2014) and Buddhika Rathnayake et al (Rathnayake et al., 2019). Thus, the HPLC analysis (**Fig. 6c**) of BPA solution treated by CWAQ using Fe/NiP at 140°C after 180 min revealed the formation of two intermediates: 4'-hydroxyacetophenone and 1,2-bis(4-hydroxyphenyl)-2-propanol.

Fig. 5: (a) Kinetics of BPA conversion (%), (b) HPLC chromatograms focused on BPA without catalyst at 140°C (c) using NiP, (d) using Fe/NiP.

Fig.6: Intermediates detection by HPLC analysis during CWAO of BPA: (a) comparison between the blank test at 140°C, NiP and Fe/NiP after 180 min of reaction, (b) comparison between NiP and Fe/NiP after 180 min of reaction, (c) comparison after 0 and 180 min reaction time for Fe/NiP.

3.2.3. Kinetic modeling of CWAO reaction of BPA

The kinetics of BPA CWAO reaction was modeled according to the pseudo-first-order (PFO) rate-law. The measured data were fitted by using a non-linear model, according to the following equation (Equ.1):

$$C(t) = C_{tot}(1 - e^{-kt}) \quad \text{Equ.1}$$

Where the total conversion (C_{tot}) and the rate constant (k) were used as fitting parameters. The term “ t ” was the CWAO reaction time. The calculated R^2 values and the residual analysis were used as parameters to evaluate the quality of the fit. Fig. 7 displays both the experimental and fitted BPA conversion as a function of reaction time for NiP and Fe/NiP. The possible rate constants for NiP and Fe/NiP would be 0.014 and 0.020 min^{-1} , respectively. Therefore, the addition of iron to NiP clearly enhanced the conversion of BPA and the rate of reaction.

Fig. 7 Pseudo-first-order kinetic fitting of BPA conversion for NiP and Fe/NiP.

3.2.4. Stability test

In addition to being efficient for the CWAQ reaction, the catalyst must be stable under the operating conditions. To evaluate the stability of the Fe/NiP catalyst, it was reused three times in consecutive CWAQ reactions. Once the catalyst was removed from the autoclave, it was filtered, washed with ultrapure water and then dried in the oven at 60°C.

Fig. 8 shows that the BPA conversion remains at about 99% after 3 cycles. However, the efficiency of the solid declines over the multiple cycles since the % Δ TOC decreases which could be due to the accumulation of intermediates and by-products onto Fe/NiP surface. Furthermore, the ICP analysis of the remaining solution after each cycle shows negligible leaching of iron (**Table 2**), indicating high stability of iron in the prepared catalyst (Fe/NiP). Nickel leaching is also negligible: 860 ppm (0.08 wt-%) after the first cycle and around 60-75 ppm for each subsequent cycles.

Fig. 8 Catalytic performance of Fe/NiP reused three times in consecutive CWAO reactions. Conversion of BPA and TOC abatement (Δ TOC) after 180 min of reaction.

Table 2. Metal leaching after 180 min of CWAO of BPA using the catalyst Fe/NiP.

leaching	Cycle 1	Cycle 2	Cycle 3
[Fe] (ppm)	0.03	0.03	0.02
[Ni] (ppm)	859.50	60.80	74.80

The diffractograms of the catalysts after each cycle (**Fig. 9**) reveal the disappearance of the $\text{Fe}_2(\text{SO}_4)_2(\text{OH})_{0.67} \cdot x\text{H}_2\text{O}$ (ICDD: 00-053-1056) phase and the appearance of a new $\text{Fe}_3(\text{PO}_4)_2(\text{OH})_2$ (ICDD: 00-014-0569) phase. The $\text{Ni}_3(\text{PO}_4)_2$ (ICDD: 00-038-1473) phase is also present in either crystalline or amorphous form, which seems to promote the conversion of BPA. In order to verify the synergistic effect between the iron phase and the nickel phase, an FeP catalyst was prepared using the same method of preparation as for the NiP catalyst. This catalyst was then evaluated for the CWAO of BPA. The results obtained are summarized in **Table 3**. Although the FeP catalyst has a high conversion of BPA, very close to that of Fe/NiP, the presence of the nickel phase in Fe/NiP results in a higher Δ TOC, around 85.0%. It can be concluded that the iron phase enables almost total conversion of BPA, but the addition of nickel is necessary to promote total oxidation.

Fig. 9 XRD patterns of Fe/NiP after 180 min of CWAO of BPA for three cycles.

Table 3. Conversion of Bisphenol A and Δ TOC after 180 min at 140 °C.

Sample	BPA conversion (%)	% Δ TOC
NiP	37.0	35.0
Fe/NiP	99.6	85.0
FeP	99.7	64.4

3.2.5. Comparison of our results to other works

Table 4 provides a comparison of our results with those reported in the literature for the CWAO of BPA. It appears that the Fe/NiP material has better catalytic performance, both in terms of conversion and TOC abatement (Δ TOC).

Table 4. Comparison of CWAO of BPA conversion and Δ TOC on different catalysts.

Catalyst	BPA initial concentration (mg/L)	Temperature (°C)	Time (min)	Conversion (%)	% Δ TOC	References
CeO ₂	60	160	180	76	75	(Heponiemi et al., 2015)
Ce _{0.85} Zr _{0.15} O ₂	60	160	180	76	73	(Heponiemi et al., 2015)

Titanate nanotube	10	200	Several hours	91	69	(Kaplan et al., 2014b)
Ru/CNS	20	130	90	>99	nd	(Serra-Pérez et al., 2019)
Pt/0.8Ti-0.2Ce	60	160	180	72	48	(Rathnayake et al., 2019)
Fe/NiP	300	140	180	>99	85	This work

4. Conclusion

The catalytic wet air oxidation of BPA was investigated by nickel phosphate as support (NiP) and iron supported on NiP as a catalyst. The conversion of BPA was studied at 140°C and 25 bar of total pressure. The CWAQ reaction using Fe/NiP catalyst was effective in achieving almost complete conversion of BPA in 180 min of reaction. Moreover, Fe/NiP catalyst showed rather high stability given the severe operating conditions (acidic media, high pressure, high temperature) and was still highly effective in successive runs. We also demonstrated that FeP and Fe/NiP have high and similar activity, but the presence of the Ni phase (Ni₃(PO₄)₂) leads to a higher ΔTOC. Studies are still ongoing in order to provide further insight into the CWAQ of BPA for possible practical application.

Conflict of interest

The authors declare no conflict of interest

References

- Ahmadi, M., Rahmani, H., Takdastan, A., Jaafarzadeh, N., Mostoufi, A., 2016. A novel catalytic process for degradation of bisphenol A from aqueous solutions: A synergistic effect of nano-Fe₃O₄@Alg-Fe on O₃/H₂O₂. *Process Saf. Environ. Prot.* 104, 413–421. <https://doi.org/10.1016/j.psep.2016.09.008>
- Akbari, S., Ghanbari, F., Moradi, M., 2016. Bisphenol A degradation in aqueous solutions by electrogenerated ferrous ion activated ozone, hydrogen peroxide and persulfate: Applying low current density for oxidation mechanism. *Chem. Eng. J.* 294, 298–307. <https://doi.org/10.1016/j.cej.2016.02.106>
- Anastopoulos, I., Anagnostopoulos, V.A., Bhatnagar, A., Mitropoulos, A.C., Kyzas, G.Z., 2017. A review for chromium removal by carbon nanotubes. *Chem. Ecol.* 33, 572–588. <https://doi.org/10.1080/02757540.2017.1328503>

354 Arampatzidou, A., Voutsas, D., Deliyanni, E., 2018. Removal of bisphenol A by Fe-impregnated
355 activated carbons. *Environ. Sci. Pollut. Res. Int.* 25, 25869–25879.
356 <https://doi.org/10.1007/s11356-018-2652-4>

357 Athalathil, S., Erjavec, B., Kaplan, R., Stüber, F., Bengoa, C., Font, J., Fortuny, A., Pintar, A.,
358 Fabregat, A., 2015. TiO₂-sludge carbon enhanced catalytic oxidative reaction in
359 environmental wastewaters applications. *J. Hazard. Mater.* 300, 406–414.
360 <https://doi.org/10.1016/j.jhazmat.2015.07.025>

361 Ben-Jonathan, N., Steinmetz, R., 1998. Xenoestrogens: the emerging story of bisphenol a. *Trends*
362 *Endocrinol. Metab.* TEM 9, 124–128. [https://doi.org/10.1016/s1043-2760\(98\)00029-0](https://doi.org/10.1016/s1043-2760(98)00029-0)

363 Bui, P., Cecilia, J.A., Oyama, S.Ted., Takagaki, A., Infantes-Molina, A., Zhao, H., Li, D.,
364 Rodríguez-Castellón, E., Jiménez López, A., 2012. Studies of the synthesis of transition
365 metal phosphides and their activity in the hydrodeoxygenation of a biofuel model
366 compound. *J. Catal.* 294, 184–198. <https://doi.org/10.1016/j.jcat.2012.07.021>

367 Chapin, R.E., Adams, J., Boekelheide, K., Gray, L.E., Hayward, S.W., Lees, P.S.J., McIntyre, B.S.,
368 Portier, K.M., Schnorr, T.M., Selevan, S.G., Vandenberg, J.G., Woskie, S.R., 2008. NTP-
369 CERHR expert panel report on the reproductive and developmental toxicity of bisphenol A.
370 *Birth Defects Res. B. Dev. Reprod. Toxicol.* 83, 157–395.
371 <https://doi.org/10.1002/bdrb.20147>

372 Chen, J., Shi, H., Li, L., Li, K., 2014. Deoxygenation of methyl laurate as a model compound to
373 hydrocarbons on transition metal phosphide catalysts. *Appl. Catal. B Environ.* 144, 870–
374 884. <https://doi.org/10.1016/j.apcatb.2013.08.026>

375 Chouhan, S., Prakash, J., Swati, Singh, S.P., 2014. Effect of Bisphenol A on human health and its
376 degradation by microorganisms: a review. *Ann. Microbiol.* 64, 13–21.
377 <https://doi.org/10.1007/s13213-013-0649-2>

378 Cleveland, V., Bingham, J.-P., Kan, E., 2014. Heterogeneous Fenton degradation of bisphenol A by
379 carbon nanotube-supported Fe₃O₄. *Sep. Purif. Technol.* 133, 388–395.
380 <https://doi.org/10.1016/j.seppur.2014.06.061>

381 Erjavec, B., Kaplan, R., Djinović, P., Pintar, A., 2013. Catalytic wet air oxidation of bisphenol A
382 model solution in a trickle-bed reactor over titanate nanotube-based catalysts. *Appl. Catal. B*
383 *Environ.* 132–133, 342–352. <https://doi.org/10.1016/j.apcatb.2012.12.007>

384 Gültekin, I., Ince, N.H., 2007. Synthetic endocrine disruptors in the environment and water
385 remediation by advanced oxidation processes. *J. Environ. Manage.* 85, 816–832.
386 <https://doi.org/10.1016/j.jenvman.2007.07.020>

387 Heponiemi, A., Azalim, S., Hu, T., Lassi, U., 2015. Cerium Oxide Based Catalysts for Wet Air
 388 Oxidation of Bisphenol A. *Top. Catal.* 58, 1043–1052. [https://doi.org/10.1007/s11244-015-](https://doi.org/10.1007/s11244-015-0457-y)
 389 0457-y

390 Kaplan, R., Erjavec, B., Senila, M., Pintar, A., 2014a. Catalytic wet air oxidation of bisphenol A
 391 solution in a batch-recycle trickle-bed reactor over titanate nanotube-based catalysts.
 392 *Environ. Sci. Pollut. Res.* 21, 11313–11319. <https://doi.org/10.1007/s11356-014-3042-1>

393 Kaplan, R., Erjavec, B., Senila, M., Pintar, A., 2014b. Catalytic wet air oxidation of bisphenol A
 394 solution in a batch-recycle trickle-bed reactor over titanate nanotube-based catalysts.
 395 *Environ. Sci. Pollut. Res. Int.* 21, 11313–11319. <https://doi.org/10.1007/s11356-014-3042-1>

396 Keav, S., de los Monteros, A.E., Barbier, J., Duprez, D., 2014. Wet Air Oxidation of phenol over Pt
 397 and Ru catalysts supported on cerium-based oxides: Resistance to fouling and kinetic
 398 modelling. *Appl. Catal. B Environ.* 150–151, 402–410.
 399 <https://doi.org/10.1016/j.apcatb.2013.12.028>

400 Kim, K.-H., Ihm, S.-K., 2011. Heterogeneous catalytic wet air oxidation of refractory organic
 401 pollutants in industrial wastewaters: A review. *J. Hazard. Mater.* 186, 16–34.
 402 <https://doi.org/10.1016/j.jhazmat.2010.11.011>

403 Lane, R.F., Adams, C.D., Randtke, S.J., Carter, R.E., 2015. Chlorination and chloramination of
 404 bisphenol A, bisphenol F, and bisphenol A diglycidyl ether in drinking water. *Water Res.*
 405 79, 68–78. <https://doi.org/10.1016/j.watres.2015.04.014>

406 Lee, S., Liao, C., Song, G.-J., Ra, K., Kannan, K., Moon, H.-B., 2015. Emission of bisphenol
 407 analogues including bisphenol A and bisphenol F from wastewater treatment plants in
 408 Korea. *Chemosphere* 119, 1000–1006. <https://doi.org/10.1016/j.chemosphere.2014.09.011>

409 Levec, J., Pintar, A., 2007. Catalytic wet-air oxidation processes: A review. *Catal. Today* 124, 172–
 410 184. <https://doi.org/10.1016/j.cattod.2007.03.035>

411 Lobos, J.H., Leib, T.K., Su, T.M., 1992. Biodegradation of bisphenol A and other bisphenols by a
 412 gram-negative aerobic bacterium. *Appl. Environ. Microbiol.* 58, 1823–1831.

413 Mirzaee, S.A., Jaafarzadeh, N., Jorfi, S., Gomes, H.T., Ahmadi, M., 2018. Enhanced degradation of
 414 Bisphenol A from high saline polycarbonate plant wastewater using wet air oxidation.
 415 *Process Saf. Environ. Prot.* 120, 321–330. <https://doi.org/10.1016/j.psep.2018.09.021>

416 Mohapatra, D.P., Brar, S.K., Tyagi, R.D., Surampalli, R.Y., 2010. Physico-chemical pre-treatment
 417 and biotransformation of wastewater and wastewater Sludge – Fate of bisphenol A.
 418 *Chemosphere* 78, 923–941. <https://doi.org/10.1016/j.chemosphere.2009.12.053>

419 Moussavi, G., Pourakbar, M., Shekoohiyan, S., Satari, M., 2018. The photochemical decomposition
 420 and detoxification of bisphenol A in the VUV/H₂O₂ process: Degradation, mineralization,

421 and cytotoxicity assessment. Chem. Eng. J. 331, 755–764.
 422 <https://doi.org/10.1016/j.cej.2017.09.009>

423 Noursir, S., Keav, S., Barbier, J., Bensitel, M., Brahmi, R., Duprez, D., 2008. Deactivation
 424 phenomena during catalytic wet air oxidation (CWAO) of phenol over platinum catalysts
 425 supported on ceria and ceria–zirconia mixed oxides. Appl. Catal. B Environ. 84, 723–731.
 426 <https://doi.org/10.1016/j.apcatb.2008.06.010>

427 Omoike, A., Wacker, T., Navidonski, M., 2013. Biodegradation of bisphenol A by *Heliscus*
 428 *lugdunensis*, a naturally occurring hyphomycete in freshwater environments. Chemosphere
 429 91, 1643–1647. <https://doi.org/10.1016/j.chemosphere.2012.12.045>

430 Pan, Z., Wang, R., Nie, Z., Chen, J., 2016. Effect of a second metal (Co, Fe, Mo and W) on
 431 performance of Ni₂P/SiO₂ for hydrodeoxygenation of methyl laurate. J. Energy Chem. 25,
 432 418–426. <https://doi.org/10.1016/j.jechem.2016.02.007>

433 Pintar, A., Batista, J., Tišler, T., 2008. Catalytic wet-air oxidation of aqueous solutions of formic
 434 acid, acetic acid and phenol in a continuous-flow trickle-bed reactor over Ru/TiO₂ catalysts.
 435 Appl. Catal. B Environ. 84, 30–41. <https://doi.org/10.1016/j.apcatb.2008.03.001>

436 Rathnayake, B., Heponiemi, A., Huovinen, M., Ojala, S., Pirilä, M., Loikkanen, J., Azalim, S.,
 437 Saouabe, M., Brahmi, R., Vähäkangas, K., Lassi, U., Keiski, R.L., 2019. Photocatalysis and
 438 catalytic wet air oxidation: Degradation and toxicity of bisphenol A containing wastewaters.
 439 Environ. Technol. 1–12. <https://doi.org/10.1080/09593330.2019.1604817>

440 Reddy, P.V.L., Kim, K.-H., 2015. A review of photochemical approaches for the treatment of a
 441 wide range of pesticides. J. Hazard. Mater. 285, 325–335.
 442 <https://doi.org/10.1016/j.jhazmat.2014.11.036>

443 Sasaki, M., Akahira, A., Oshiman, K., Tsuchido, T., Matsumura, Y., 2005a. Purification of
 444 Cytochrome P450 and Ferredoxin, Involved in Bisphenol A Degradation, from
 445 *Sphingomonas* sp. Strain AO1. Appl. Environ. Microbiol. 71, 8024–8030.
 446 <https://doi.org/10.1128/AEM.71.12.8024-8030.2005>

447 Sasaki, M., Maki, J., Oshiman, K., Matsumura, Y., Tsuchido, T., 2005b. Biodegradation of
 448 bisphenol A by cells and cell lysate from *Sphingomonas* sp. strain AO1. Biodegradation 16,
 449 449–459. <https://doi.org/10.1007/s10532-004-5023-4>

450 Serra-Pérez, E., Álvarez-Torrellas, S., Ismael Águeda, V., Delgado, J.A., Ovejero, G., García, J.,
 451 2019. Insights into the removal of Bisphenol A by catalytic wet air oxidation upon carbon
 452 nanospheres-based catalysts: Key operating parameters, degradation intermediates and
 453 reaction pathway. Appl. Surf. Sci. 473, 726–737.
 454 <https://doi.org/10.1016/j.apsusc.2018.12.205>

- 455 Sing, K.S.W., 1985. Reporting physisorption data for gas/solid systems with special reference to the
456 determination of surface area and porosity (Recommendations 1984). *Pure Appl. Chem.* 57,
457 603–619. <https://doi.org/10.1351/pac198557040603>
- 458 Staples, C.A., Dome, P.B., Klecka, G.M., Oblock, S.T., Harris, L.R., 1998. A review of the
459 environmental fate, effects, and exposures of bisphenol A. *Chemosphere* 36, 2149–2173.
460 [https://doi.org/10.1016/S0045-6535\(97\)10133-3](https://doi.org/10.1016/S0045-6535(97)10133-3)
- 461 Tai, C., Jiang, G., Liu, Jingfu, Zhou, Q., Liu, Jiyan, 2005. Rapid degradation of bisphenol A using
462 air as the oxidant catalyzed by polynuclear phthalocyanine complexes under visible light
463 irradiation. *J. Photochem. Photobiol. Chem.* 172, 275–282.
464 <https://doi.org/10.1016/j.jphotochem.2004.12.015>
- 465 Thommes, M., 2010. Physical Adsorption Characterization of Nanoporous Materials. *Chem. Ing.*
466 *Tech.* 82, 1059–1073. <https://doi.org/10.1002/cite.201000064>
- 467 Vandenberg, L.N., Hauser, R., Marcus, M., Olea, N., Welshons, W.V., 2007. Human exposure to
468 bisphenol A (BPA). *Reprod. Toxicol.* 24, 139–177.
469 <https://doi.org/10.1016/j.reprotox.2007.07.010>
- 470 Zbair, M., Ainassaari, K., El Assal, Z., Ojala, S., El Ouahedy, N., Keiski, R.L., Bensitel, M.,
471 Brahmi, R., 2018. Steam activation of waste biomass: highly microporous carbon,
472 optimization of bisphenol A, and diuron adsorption by response surface methodology.
473 *Environ. Sci. Pollut. Res.* 25, 35657–35671. <https://doi.org/10.1007/s11356-018-3455-3>
- 474 Zhang, Z., Huang, J., Xia, H., Dai, Q., Gu, Y., Lao, Y., Wang, X., 2018. Chlorinated volatile
475 organic compound oxidation over SO₄²⁻/Fe₂O₃ catalysts. *J. Catal.* 360, 277–289.
476 <https://doi.org/10.1016/j.jcat.2017.11.024>
- 477 Zou, X., Chen, T., Zhang, P., Chen, D., He, J., Dang, Y., Ma, Z., Chen, Y., Toloueinia, P., Zhu, C.,
478 Xie, J., Liu, H., Suib, S.L., 2018. High catalytic performance of Fe-Ni/Palygorskite in the
479 steam reforming of toluene for hydrogen production. *Appl. Energy* 226, 827–837.
480 <https://doi.org/10.1016/j.apenergy.2018.06.005>